Application No. 10/049,610 Attorney Docket No. 041301-0284989

Amendments to the Claims:

This listing of claims replaces all prior versions and listings of claims in this application:

703-905-2500

1. (Previously Presented) A thermal transfer medium comprising a substrate bearing on at least part of one surface thereof a coating layer of a thermally transferable overlay material for transfer onto a thermal transfer image formed on a receiver material, wherein the coating layer comprises a hydroxy-terminated polyester having a Tg of at least 75° C and a molecular weight ranging from 6,000 to 10,000, and wherein a cross-linked acrylic subcoat is present between the substrate and coating.

2. (Cancelled)

- 3. (Previously Presented). A thermal transfer medium according to claim 1, wherein the polyester has a Tg of about 80°C and a molecular weight ranging from about 7,000 to 10,000.
- 4. (Previously Presented) A thermal transfer medium according to claim 1, wherein the polyester has a Tg of about 77°C and a molecular weight ranging from about 7,500 to 10,000.
- 5. (Previously Presented) A thermal transfer medium according to claim 1, wherein the coating further comprises filler material.
- 6. (Previously Presented) A thermal transfer medium according to claim 1, wherein the coating further comprises one or more ultra-violet light absorbers.
- 7. (Previously Presented) A thermal transfer medium according to claim 1, wherein the coating further comprises one or more optical brighteners.

Application No. 10/049,610 Attorney Docket No. 041301-0284989 Page 3

- 8. (Previously Presented) A thermal transfer medium according to claim 1, wherein the substrate comprises a film of heat-resistant material selected from polyesters, polyamides, polyimides, polycarbonates, polysulphones, polypropylene and cellophane.
- 9. (Previously Presented) A thermal transfer medium according to claim 1, wherein the coating has a thickness ranging from 0.5 to 5.0µm.
 - 10-11 (Cancelled).
- 12. (Previously Presented) A thermal transfer medium according to claim 1, wherein the other surface of the substrate has a heat-resistant backcoat.
- 13. (Currently Amended) A thermal transfer medium, comprising an elongate strip of substrate material having on one surface thereof a plurality of similar sets of thermally transferable dye coats and mass transfer layers, each set comprising a respective coat of dye colors, yellow, magenta and cyan, and a respective mass transfer layer for colorant and overlay, each coat or layer being in the form of a discrete stripe extending transverse to the length of the substrate, wherein each overlay material mass transfer layer comprises a coating of an overlay material comprising a hydroxy-terminated polyester having a glass transition temperature (Tg) greater than 50° C and a molecular weight ranging from 6,000 to 10,000, and wherein a cross-linked acrylic subcoat is present between the substrate and coating.

14. Cancelled

15. (Previously Presented) A method of forming an overlay on a receiver material, comprising the steps of

superposing a thermal transfer medium in accordance with claim 1 and a receiver material;

applying localized heating to the thermal transfer medium

to form an overlay on the receiver material.

From-PILLSBURY WINTHROP

- 16. (Previously Presented) A method according to claim 15, further comprising the step of producing a printed image on the receiver material by thermal transfer printing prior to formation of the overlay.
 - 17. (Cancelled).
- 18. (Currently Amended) A method according to claim 15, wherein the receiver material comprises Receiver material according to claim 17, comprising a card of polyvinyl chloride.
- 19. (Currently Amended) A method Receiver material according to claim 15 17, wherein the receiver material has an image-receiving surface comprising vinyl chloride/vinyl acetate copolymer.
- 20. (Currently Amended) A method Receiver material according to claim 17 15, wherein the receiver is in the form of an identification card bearing a full color image produced by thermal transfer printing and text and/or a bar code produced by mass transfer printing of colorant.
- 21. (Previously Presented) The combination of a receiver material having an imagereceiving surface comprising vinyl chloride/vinyl acetate copolymer and a thermal transfer
 medium comprising a substrate bearing on at least part of one surface thereof a coating layer of a
 thermally transferable overlay material for transfer onto a thermal transfer image formed on the
 receiver material, wherein the coating layer comprises polyester having a Tg greater than 50° C
 and a molecular weight ranging from 6,000 to 10,000.
- 22. (Previously Presented) A combination according to claim 21, wherein the receiver material comprises a card of polyvinyl chloride.

From-PILLSBURY WINTHROP

Application No. 10/049,610 Attorney Docket No. 041301-0284989 Page 5

- 23. (Previously Presented) Receiver material having an image-receiving surface comprising vinyl chloride/vinyl acetate copolymer on which has been formed an overlay by applying localized heating to a thermal transfer medium comprising a substrate bearing on at least part of one surface thereof a coating layer of a thermally transferable overlay material for transfer onto a thermal transfer image formed on a receiver material, wherein the coating layer comprises polyester having a Tg greater than 50° C and a molecular weight ranging from 6,000 to 10,000.
- 24. (Previously Presented) Receiver material according to claim 23, wherein the receiver material comprises a card of polyvinyl chloride.
- 25. (Previously Presented) Receiver material according to claim 23, bearing a printed image formed on the image-receiving surface prior to formation of the overlay.
- 26. (Previously Presented) A method of forming an overlay on a receiver material having an image-receiving surface comprising vinyl chloride/vinyl acetate copolymer, comprising the steps of

superimposing a thermal transfer medium comprising a substrate bearing on at least part of one surface thereof a coating layer of a thermally transferable overlay material for transfer onto a thermal transfer image formed on a receiver material, wherein the coating layer comprises polyester having a Tg greater than 50° C and a molecular weight ranging from 6,000 to 10,000; and

applying localized heating to the thermal transfer medium to form an overlay on the receiver material.

27. (New) Receiver material according to claim 23, wherein the receiver material is in the form of an identification card bearing a full color image produced by thermal transfer printing and text and/or a bar code produced by mass transfer printing of colorant.